

**Product Name:** Final Cut 601

**Description:** AUTOTRIZ Final Cut 601 is the all-new formula for the professionals. Formulated with super-micro abrasive technology, it delivers quick cut and high gloss simultaneously. This unique formula has longer working cycle to save product consumption. Virtually no dust or slings.



Technical Data		General Data	
<b>Appearance</b>	Cream	<b>Product</b>	Final Cut 601
<b>Cut</b>	6/10	<b>Group</b>	Polishing
<b>Gloss</b>	>6	<b>Category</b>	Alternative
<b>Speed</b>	Alternative	<b>Volume</b>	1L (AT-PC-601)
<b>Pressure</b>	Moderate	<b>Application</b>	Body Paint
<b>Abrasive effect</b>	Swirl removal	<b>Complimentary</b>	Wool/Foam Pad
<b>Specified Gravity</b>	1.20 g/cm <sup>3</sup>	<b>Industries</b>	Detailing/Paint shops
<b>Hazard</b>	Non-Hazardous	<b>Storage</b>	5-35°C/41-95°F

**Directions:** Shake bottle well before use. Work on a cool and clean surface.

DA Application: Apply product to the AUTOTRIZ Fine Cut Wool Pad (AT-WP-FC), or Fine Cut Foam Pad (AT-FP-FC). Set machine speed to 4-5, Apply moderate to light pressure with 3-5 overlapping passes until desired cutting result is achieved.

Rotary Application: Set rotary polisher speed to 1500-2000RPM. Use AUTOTRIZ Fine Cut Wool Pad (AT-WP-FC) or Fine Cut Foam Pad (AT-FP-FC). Apply product on paint surface directly, work on 2'x2' area at each time. Apply moderate to light pressure with 3-5 overlapping passes until scratches and sanding marks are removed.

Removes residue with a AUTOTRIZ Microfiber Cloth Ultrafine (AT-MT40). For the absolute best results, follow AUTOTRIZ Supreme Polish (AT-PC-402) and AUTOTRIZ Ultimate Polish (AT-PC-302).

**Tips:** Clean pads frequently. Use AUTOTRIZ Surface Prep (AT-CC-SP) to remove residue and check for any defect.