

Product Name: Revo

Description: AUTOTRIZ REVO is a cutting-edge nano ceramic coating that amplifies the latest improvement in nano technology. Proven to stand out against the typical elements that will deal harm to paintwork. It fills nanopores and establishes great molecular bonds to achieve next-level durability and stability.



Coverage: Revo is suitable to be applied on car-painted surfaces, such as one (1K) or two-component (2K) paints (polyurethane or epoxy systems). The preferred use is for the exterior paint of cars, motorbikes, trucks, and buses. Per 50ML covers approximately 2 sedan cars.

| Technical Data | | General Data | |
|---|------------------------|---|---|
| Shelf life | 12 months | Product | Revo |
| Appearance | Colorless | Category | Retail Car Coating |
| Curing | Normal ambient | Volume | 50ML (AT-REV-50) |
| Base | Polysiloxane | Application | Body Paint |
| Specified Gravity | 0.86 g/cm ³ | Coverage | 50ML (5m ² - 6m ²) |
| Hazard | Non-Hazardous | Storage | 5-35°C/41-95°F |
| Properties | | Tools Needed | |
| <ul style="list-style-type: none"> • High gloss finish • Super hydrophobic • Easy-to-clean • UV & chemical resistance • Easy to apply • Cures at room temperature • 9H pencil hardness | | <ul style="list-style-type: none"> • Applicator block (AT-AC-AB) • Microfiber Suede cloth (AT-AC-MS) • Lint-free microfiber towel (AT-AC-MC) | |

Guide: The product is for consumer use, hence, can be applied by anyone that follows the simple instruction. Test on a small area or apply a test coat before application.

Instruction: Shake well before use. Get ready with 2 pieces of brand new, lint-free microfiber towel. (It is recommended that new towels to be rinsed or washed with water prior to use to reduce the loosing lint). When first applying Revo on substrate, it is recommended to condition the surface of the applicator block with 7-8 drops to prevent skipping or dry spots. Do not work on large area at a time. It is recommended to do a 2 ft. x 2 ft. area at a time with normal pressure on applicator. Make sure the area is well covered. Always start from an edge to avoid excess on other panels. Work in controlled areas to remember where you previously applied. Ensure that product is carried through consistently. Wait for 1-2 minutes. Use first towel to level the product. Go immediately over with second microfiber towel with polishing motion until the surface is free from residue. When the whole car is applied, allow curing of coating to begin.

Precaution: Ensure the substrate is free from contaminants prior to and during the application process. Keep coating away from all polish and compound dust during the curing process.

Process and Curing: The product must be applied at an ambient temperature of at least + 5°C and relative humidity of 30 % - 80 %. Avoid direct sunlight! Apply the coating in clean and dry conditions. Any mistakes can be rectified within approx. 10 min of application. Traces of water in the applicator should also be avoided. Applicators dampened with water should not be used. The applicators cannot be reused once the coating has been applied. Revo Base Coat is dry-to-touch after about one hour.